

# SS 431, Type 431, WNR 1.4057, UNS S43100, AISI 431, Grade 431, AFNOR Z20CN17.2M

## Introduction :

Aesteiron continues to expand its product line in UNS S43100 to meet the emerging customer needs, and whereas Aesteiron Steels Pvt. Ltd. is ISO 9001 : 2008 Certified, ASPL has a great Projects in this grade in all parts of the world with renowned suppliers presenting the wide range of services. We pride ourselves in the quality of our products, our competitive pricing and our exceptional customer service. We have been recognized for our outstanding customer service in satisfaction surveys of top- ranked mills in india and all over the world. ASPL, with iron and steel as its main business, manufactures premium steel products with high technologies and a high added value and fosters three major product categories, namely carbon steel, stainless steel and special steel. Through our worldwide marketing network, these premium products not only satisfy the demand on the domestic market but are also exported to more than forty countries and regions in Asia, Africa, Europa and America, extensively applied to various. We are a highly qualified by our customers worldwide as a sustainable and trustworthy to meet their request and need at the right time and the right time and the right area. We strive and stand committed to maintain this respectable position by catering to the requirements of our customers in the best possible way leaving no room for complaints.

## Chemical Composition

	SS 431	TYPE 431	WNR 1.4057	UNS S43100	AISI 431	GRADE 431	AFNOR Z20CN17.2M
Carbon	0.20 max	0.20 max	0.20 max	0.20 max	0.20 max	0.20 max	0.20 max
Manganese	1.00 max	1.00 max	1.00 max	1.00 max	1.00 max	1.00 max	1.00 max
Phosphorus	0.04 max	0.04 max	0.04 max	0.04 max	0.04 max	0.04 max	0.04 max
Sulfur	0.03 max	0.03 max	0.03 max	0.03 max	0.03 max	0.03 max	0.03 max
Silicon	1.00 max	1.00 max	1.00 max	1.00 max	1.00 max	1.00 max	1.00 max
Chromium	15.0-18.0	15.0-18.0	15.0-18.0	15.0-18.0	15.0-18.0	15.0-18.0	15.0-18.0
Nickel	1.25-3.00	1.25-3.00	1.25-3.00	1.25-3.00	1.25-3.00	1.25-3.00	1.25-3.00

## Mechanical Properties

	SS 431	TYPE 431	WNR 1.4057	UNS S43100	AISI 431	GRADE 431	AFNOR Z20CN17.2M
Tensile Strength, Mpa	940	940	940	940	940	940	940
0.2% Yield Strength, Mpa	750	750	750	750	750	750	750
Elongation in 2" in 50mm%	19	19	19	19	19	20 min	20 min

## Standard Available in forms :

- ASTM A182/ ASME SA182 Stainless Steel Pipe Fittings
- ASTM A213 / ASME SA213 Seamless Stainless Steel Pipes
- ASTM A240/ ASME SA240 Stainless Steels Sheets / Plates
- ASTM A249/ ASME SA249 Stainless Steel Welded Tubes
- ASTM A269/ ASME SA269 Stainless Steel Tubes
- ASTM A270/ ASME SA270 Stainless Steel Sanitary Tubes
- ASTM A312/ ASME SA312 Stainless Steel Pipes
- ASTM A403/ ASME SA403 Stainless Steel Pipe Fittings
- ASTM A554/ ASME SA554 Stainless Steel Welded Tubes
- ASTM A731/ ASME SA731 Stainless Steel Pipes
- ASTM A789/ ASME SA789 Stainless Steel Tubes
- ASTM A790/ ASME SA790 Stainless Steel Pipes
- ASTM A791/ ASME SA791 Stainless Steel Tubes

## Products Available in forms :

- SS 431, Type 431, WNR 1.4057, UNS S43100, AISI 431 Plates
- SS 431, Type 431, WNR 1.4057, UNS S43100, AISI 431 Pipes
- SS 431, Type 431, WNR 1.4057, UNS S43100, AISI 431 Round Bar
- SS 431, Type 431, WNR 1.4057, UNS S43100, AISI 431 Tube
- SS 431, Type 431, WNR 1.4057, UNS S43100, AISI 431 Flanges
- SS 431, Type 431, WNR 1.4057, UNS S43100, AISI 431 Wire
- SS 431, Type 431, WNR 1.4057, UNS S43100, AISI 431 Fittings

## Corrosion Resistance

- Grade 431 stainless steels have considerable resistance to salt water, but they are less resistant to tropical water when compared to that of grade 316 steels.
- Grade 431 steels have overall corrosion resistance similar to, or slightly lower than, that of grade 304 steels.
- Grade 431 steels with a smooth surface finish perform well in tempered and hardened conditions.

## Heat Resistance

- Grade 431 steels are resistant to scaling at temperatures of 925°C in intermittent conditions, and 870°C during continuous operations.
- In general, these steels are not to be used at temperatures above standard tempering temperatures, owing to loss of mechanical properties.

"Aesteiron House", 107, Kika Street, 4th Floor, Gulawadi, Mumbai - 400 004, India.

[info@aesteironsteelpipes.com](mailto:info@aesteironsteelpipes.com)

[www.aesteironsteelpipes.com](http://www.aesteironsteelpipes.com)

© 2016-17. The content on this website is owned by Registrant of domain <http://aesteironsteelpipes.com/> , Do not copy any content (including images) without prior written consent. Manufacturer, Stockholder, Suppliers, Traders, Wholesaler, Dealer, Distributor, Importer, Exporter, Stockiest of Alloy Steel Pipe Tubes, Stainless Steel Pipe Tube & Carbon Steel Pipe Tube



## Heat Treatment

### Full anneal —

- Full annealing cannot be performed on grade 431 steels.
- This grade gets hardened even during slow cooling.

### Process anneal —

- Grade 431 steels are heated to 620 to 660°C and then air-cooled.
- Grade 431 steels are generally hardened by heating at temperatures from 980 to 1065°C, holding for nearly ½ h, followed by oil or air quenching.
- Complex or hardened parts of grade 431 steels can be pre-heated to temperatures from 760 to 790°C and tempered, to improve their mechanical properties.
- Tempering of these steels at 425 to 600°C should be avoided, owing to the loss of impact toughness at this temperature range.

## Welding

- Welding of grade 431 stainless steels is difficult due to the chances of cracking.
- It is recommended to pre-heat the materials to 200 - 300°C before welding, and carry out post-weld heat treatment at 650°C.
- Welding can be performed using grade 410 filler rods, but ductile welds can be achieved using grades 308L, 309 or 310 steels.

## Machining

- Grade 431 steels can be easily machined in their annealed state.
- However, it is extremely difficult to machine these steels if they are hardened above 30HRC.

## Applications

- Laboratory equipment
- Marine systems
- Beater bars
- Pump and propeller shafts
- Nuts and bolts



"Aesteiron House", 107, Kika Street, 4th Floor, Gulalwadi, Mumbai - 400 004, India.

[info@aesteironsteelpipes.com](mailto:info@aesteironsteelpipes.com)

[www.aesteironsteelpipes.com](http://www.aesteironsteelpipes.com)

© 2016-17. The content on this website is owned by Registrant of domain <http://aesteironsteelpipes.com/> , Do not copy any content (including images) without prior written consent. Manufacturer, Stockholder, Suppliers, Traders, Wholesaler, Dealer, Distributor, Importer, Exporter, Stockiest of Alloy Steel Pipe Tubes, Stainless Steel Pipe Tube & Carbon Steel Pipe Tube